



CHARACTERISTICS

- High quality plasto-elastic repair sealant
- With coarse grain structure
- Can be painted once sufficiently cured
- Phthalate free

APPLICATIONS

- For repairing cracks and filling holes in walls
- For repairing joints between bricks and façade masonry
- Also appropriate for joints on walls, window sills, etc.
- Appropriate for all porous surfaces such as structure plaster, stone, concrete, wood, etc.

TECHNICAL CHARACTERISTICS	
Uncured sealant	
Type of sealant	Acrylic sealant
Appearance	Roughly granulated structure
Vulcanising system	Evaporation of water
Skin forming time (23°C and 50% R.H.)	20 min
Curing speed (23°C and 50% R.H.)	0,5 mm/24 hours
Density : ISO 1183	1,93 g/ml
Processing temperature	+5°C - +40°C
Shelf life, in the original packing in dry conditions between +5°C - +25°C	Min. 12 months
Cured sealant	
Shore A hardness : ISO 868	40
Elastic recovery : ISO 7389	<50%
Deformation capability : ISO 11600	7,5%
Modulus at 100% elongation : ISO 8340	0,13 N/mm ²
% Elongation at break : ISO 8339	>100%
Temperature resistance	-20°C - +80°C.

PACKING AND COLOURS
12 cartridges of 310 ml/box (with V-nozzle) - 104 boxes/pallet
Cement grey, ral 1015

Other colours are available on request (75 cartridges or multiples).

METHOD OF USE

Preparation

All surfaces should be dry, clean and free from dust or grease. When necessary, degrease with **Parasilico Cleaner**, MEK, alcohol or ethanol. If necessary, use a primer. It is recommended that adhesion tests are done to determine the suitability of the product for its application

Application

With a gun (manual or pneumatic). The shape of the joint is important. Avoid thin layers.

Parafix Cement Repair vulcanizes by evaporation of water. As long as less than 90% of the joints are vulcanised, maximum 5% movement is allowed.

This technical data sheet replaces all previous editions. The data on this sheet have been compiled according to the last laboratory report. Technical characteristics can be changed or adapted. We are not responsible for any incomplete information. Before use, one needs to ensure that the product is suitable for his application. Therefore, tests are necessary. Our general conditions apply.

Tooling

Smoothen with **DL 100** (before skin forming).

Cleaning

Tools: With water before it is dry.

Repairing

With the same product.

SAFETY

Safety data sheet available on request.

LIMITATIONS

- Cannot be used for joints that are permanently exposed to water
- Protect against frost. Do not apply in case of risk of rain and frost

TECHNICAL APPROVALS



* Information sur le niveau d'émission de substances volatiles dans l'air intérieur, présentant un risque de toxicité par inhalation, sur une échelle de classe allant de A+ (très faibles émissions) à C (fortes émissions).

This technical data sheet replaces all previous editions. The data on this sheet have been compiled according to the last laboratory report. Technical characteristics can be changed or adapted. We are not responsible for any incomplete information. Before use, one needs to ensure that the product is suitable for his application. Therefore, tests are necessary. Our general conditions apply.