



CHARACTERISTICS

- One-pack, plastic sealant
- Based on linseed and soya oil
- Good adhesion on most surfaces
- Forms a skin but does not harden
- Does not stain on porous materials
- Is paintable with paint based on solvent
- Outstanding weathering properties

APPLICATIONS

- Can be used for sealing of connecting joints in the building industry, around doors and frames, etc.
- Can be used for all joints with poor elongation (max. 7,8 %).

TECHNICAL CHARACTERISTICS	
Type of sealant	Polybutene
Vulcanising system	Oxidative drying
Skin forming time (23°C and 50% R.H.)	Within 24 hours
Density: ISO 1183	1,5 g/ml
Processing temperature	+1°C - +35°C
Shelf life, in the original packing in dry conditions between +5°C - +25°C	12 months
Temperature resistance	-20°C - +80°C

PACKING AND COLOURS
25 cartridges of 310 ml/box - 48 boxes/pallet
Cream, grey

METHOD OF USE

Preparation

All surfaces should be dry, clean and free from dust or grease. When necessary, degrease with **Parasilico Cleaner**, MEK, alcohol or ethanol. If necessary, use a primer. It is recommended to carry out preliminary tests in order to determine the suitability of the product for its application.

Joint dimension

Max. Joint dimensions 10 x 10 mm.

Tooling

If desired, smooth surface before skin formation with the tooling agent **DL 100** and a scraper.

Cleaning

With white-spirit or toluene

SAFETY

Safety data sheet available on request.



* Information sur le niveau d'émission de substances volatiles dans l'air intérieur, présentant un risque de toxicité par inhalation, sur une échelle de classe allant de A+ (très faibles émissions) à C (fortes émissions).

This technical data sheet replaces all previous editions. The data on this sheet have been compiled according to the last laboratory report. Technical characteristics can be changed or adapted. We are not responsible for any incomplete information. Before use, one needs to ensure that the product is suitable for his application. Therefore, tests are necessary. Our general conditions apply.