PARACRYL PARQUET



CHARACTERISTICS

- Plasto-elastic acrylic sealing kit
- Available in a variety of wood colour tones
- Instant adhesion on all clean and dry surfaces.
- Remains permanently flexible
- Can be painted when cured
- Solvent and phthalate free

APPLICATIONS

- Can be used for the sealing of connection joints on parquet and laminated floors and of connection joints between parquet and laminated floors, skirting boards and walls.
- Suitable for joints with moderate movement (maximum 12,5%).
- Suitable for all porous surfaces (wood, stone, concrete, plaster...) and metal, ceramic tiles and laminate flooring.

TECHNICAL CHARACTERISTICS	
Uncured sealant	
Type of sealant	High-quality acrylic dispersion sealant
Vulcanising system	Evaporation of water
Skin forming time (23°C and 50% R.H.)	60 - 70 min.
Vulcanisation rate (23°C and 50% R.H.)	0,5 mm after 24h
Density: ISO 1183	1,65 g/ml
Processing temperature	+5°C - +40°C
Shelf life, in the original packing in dry conditions between +5°C - +25°C	12 months
Cured sealant	
Shore A hardness: ISO 868	36
Deformation capability: ISO 11600	12,5%
Modulus at 100% elongation: ISO 8340	0,08 N/mm ²
% Elongation at break: ISO 8339	250%
Temperature resistance	-20°C - +80°C.

PACKING AND COLOURS

25 cartridges of 310 ml/box - 48 boxes/pallet

Beige, beech, dark beige, grey beige, middle oak

METHOD OF USE

Preparation

All surfaces should be dry, clean and free from dust or grease. When necessary, degrease with **Parasilico Cleaner**, MEK, or alcohol. It is recommended that apply a small test area prior to general use.

Application

With a gun (manual or pneumatic). The shape of the joint is important. Avoid thin layers.

Tooling

Smooth with water, spatula or putty knife before skin formation.

Cleaning

With water before it is dry.

This technical data sheet replaces all previous editions. The data on this sheet have been compiled according to the last laboratory report. Technical characteristics can be changed or adapted. We are not responsible for any incomplete information. Before use, one needs to ensure that the product is suitable for his application. Therefore, tests are necessary. Our general conditions apply.



1/2

Repairing

With the same product.

SAFETY

Safety data sheet available online at www.dl-chem.om

LIMITATIONS

- Cannot be used for joints that are permanently exposed to water.
- Not suitable for vinyl (PVC, LVT ...) and linoleum.
- Do not use as a glazing sealant.
- During the first days of vulcanization, a maximum movement of 5% is allowed.
- Repaintability / varnishing: first do a compatibility test. The varnishes need to be elastic.

TECHNICAL APPROVALS



14 DL Chemicals

EN 15651-1 F INT No. DoP: MP0060029



* Information sur le niveau d'émission de substances volatiles dans l'air intérieur, présentant un risque de toxicité par inhalation, sur une échelle de classe allant de A+ (très faibles émissions) à C (fortes émissions).

This technical data sheet replaces all previous editions. The data on this sheet have been compiled according to the last laboratory report. Technical characteristics can be changed or adapted. We are not responsible for any incomplete information. Before use, one needs to ensure that the product is suitable for his application. Therefore, tests are necessary. Our general conditions apply.

