



CHARACTERISTICS

- Ready for use
- Supple, bituminous fibre-reinforced adhesive
- Fast-drying
- This adhesive layer also forms a waterproof intermediate layer which improves the sealing of the roof

APPLICATIONS

- Fast adhesion without fire danger of just about all-bituminous roof rolls.
- Adhesive layer for the fixing of slate chippings and gravel to existing bituminous roof sealing, to obtain a granulated surface that protects your roof covering against UV rays and accelerated ageing.

TECHNICAL CHARACTERISTICS	
Basis	Bitumen, polymers and fibre-reinforcement, solvents.
Colour	Black
Consistency	Semi-liquid
Solvents	Petroleum hydrocarbons - with use, take necessary elementary precautionary measures.
Flash point cc : ASTM D93	43°C (Pensky Martens)
Visco 40°C : ASTM D445	2650 mm ² /s
Density	1 g/cm ³ at 20°C
Application temperature	+5°C to +30°C
Theoretic consumption	1 - 1,5 kg/m ² , depending on the porosity of the surface.
Shelf life, in unopened packing.	Min. 18 months

PACKING
Can 5 kg - 96 cans/pallet

METHOD OF USE

Preparation

The surface to be treated should be dry, dust- and grease-free.

Primers

Impregnate the surface beforehand with the fast-drying **Paraphalt Primer** (30 min). This primer can also be applied to a slightly moist surface.

Application

- Stir well before use
- Apply with a paintbrush, semi-hard squeegee or toothed comb.
- Roll out the roof rolls and press in the cold adhesive with an overlap of approx. 8 cm without adhesive.
- Seal overlaps, protruding edges and details with soft flame.

Cleaning

Clean tools with white spirit.

SAFETY

Safety data sheet available on request.

LIMITATIONS

Not suitable for roof rolls provided with burn-away foil on the underside.

This technical data sheet replaces all previous editions. The data on this sheet have been compiled according to the last laboratory report. Technical characteristics can be changed or adapted. We are not responsible for any incomplete information. Before use, one needs to ensure that the product is suitable for his application. Therefore, tests are necessary. Our general conditions apply.