



CHARACTERISTICS

- Flexible bituminous cold glue
- Reinforced by fibers
- Levels minor irregularities

APPLICATIONS

- Bonding bituminous sealing layer without fire hazard on various surfaces such as bituminous roofing, concrete, insulation, metal, etc.

TECHNICAL CHARACTERISTICS

Type of product	Bitumen with fibre reinforcement, additives and solvents
Density (g/ml)	1.15
Consistency	Liquid pasta
Viscosity	31.000 - 46.000 mPa.s (Haake 25°C)
Curing time	24 hours
Application temperature	+5°C - +35°C
Dry matter content	±80%
Shelf life of unopened product	36 months
Storage conditions	Transport and store upright in a dry, cool place at +5°C to +25°C.

PACKING AND COLOURS

can 5kg - 120 pieces/pallet
Black

METHOD OF USE

Preparation

- The surfaces must be solid, dry and free of dust and grease.
- Stir the product well.

Primers

- On a very absorbent or very dusty surface (concrete, cement, etc.) first apply a coat of Pararroof Quick Primer (drying time 30 min).

Application

- Apply in one layer.

This technical data sheet replaces all previous editions. The data on this sheet have been compiled according to the last laboratory report. Technical characteristics can be changed or adapted. We are not responsible for any incomplete information. Before use, one needs to ensure that the product is suitable for his application. Therefore, tests are necessary. Our general conditions apply

- Unroll the roofing rolls and press them into the adhesive, with 8 cm overlaps without adhesive. For detailed finishing, upstanding edges, and overlaps, bond with Pararroof Super and seal with Pararroof Super or Pararroof Bitumen.
- Apply with a floor squeegee or brush.
- Apply weight to the edges of the glued roof rolls during drying and up to one month after application for maximum results.

Consumption

1 - 1.5 kg/m² depending on the porosity of the substrate.

Cleaning

- Clean tools with white spirit.

SAFETY

Consult the safety information on the packaging and the safety data sheet for more information.

POINTS OF ATTENTION

- The use of Pararroof Cold Glue is limited to a slope of <15% of the flat roof.

This technical data sheet replaces all previous editions. The data on this sheet have been compiled according to the last laboratory report. Technical characteristics can be changed or adapted. We are not responsible for any incomplete information. Before use, one needs to ensure that the product is suitable for his application. Therefore, tests are necessary. Our general conditions apply