PARACOL STRATI G



CHARACTERISTICS

- Contact glue
- Thixotropic pasty, without dripping or smudging
- Great adhesion

APPLICATIONS

- Designed for vertical gluing.
- Can be used on laminated or stratified panels, rubber or plastic selectionnals, wood, veneering, agglomerates, plywood, fibro-cement, metals, cork, phenolic foam, polyurethane, pasted materials on concrete, asbestos cement, plaster on metal, or combination of any of these elements.
- Indoor use.

TECHNICAL CHARACTERISTICS	
Base	Polychloroprene and high quality resins in a mixture of organic solvents
Colour	Brown-beige
Viscosity	Thrixotropic
Inflammablility	Yes
Density at 20°C	0,88 g/cm ³
Temperature resistance	85°C
Shelf life, in the original packing between 15°C-20°C	Min. 18 months
Consommation	200 - 350 g/m²
Application temperature	> 10°C

PACKING
12 cans of 750 ml/box - 50 boxes/pallet
Can 5 I - 108 cans/pallet

METHOD OF USE

Preparation

- Surfaces must be dry, free of dust and any contaminating substances.
- In case of seepage or condensation, pour out few drops of solvent from the surface. This operation does not bring any damage to the quality of the product.

Application

- Spread the glue with a brush or a spatula.
- Spread a smooth layer of glue (150 g) on the two surfaces to be bonded.
- Let solvents escape (7 to 15 min. according to temperature and surfaces).
- The elements to be glued can be pressed together as soon as the glue does not stick to the fingers anymore.
- Press the two parts together very precisely as the setting power is immediate and irreversible. After the pressing it is no longer possible to correct.
- Maximum adherence is achieved after 48 to 72 hours.

Cleaning With acetone.

SAFETY Refer to the packaging or safety data sheet for additional information.

POINTS OF ATTENTION This glue cannot be used with polystyrene.

TECHNICAL APPROVALS



* Information sur le niveau d'émission de substances volatiles dans l'air intérieur, présentant un risque de toxicité par inhalation, sur une échelle de classe allant de A+ (très faibles émissions) à C (fortes émissions).

This technical data sheet replaces all previous editions. The data on this sheet have been compiled according to the last laboratory report. Technical characteristics can be changed or adapted. We are not responsible for any incomplete information. Before use, one needs to ensure that the product is suitable for his application. Therefore, tests are necessary. Our general conditions apply.

