



CHARACTERISTICS

- Universal 1-component hybrid polymer based parquet adhesive
- Ready-to-use and easy to work on, easy to spread
- Suitable for use with underfloor heating
- Permanently elastic: absorbs the working movement of parquet floors
- Better acoustic comfort
- Solvent, water, phthalate and isocyanate free
- Parquet can be treaded after 24 hours

APPLICATIONS

- Suitable for solid parquet, multi-layer parquet, mosaic parquet, industrial parquet (slat on side/slat on edge), lamparquet, chipboards and OSB.
- Suitable for solid oak parquet up to 150x40 mm.
- Suitable for the most common types of wood and particularly suitable for problematic woods such as beech, maple and bamboo.
- Suitable for bonding parquet on floors with underfloor heating.
- For both absorbent and non-absorbent surfaces.

TECHNICAL CHARACTERISTICS	
Basic ingredient	Hybrid polymer
Curing system	By means of humidity
Number of components	1
Open time (23°C and 50% R.V.)	30 min.
Curing rate (23°C and 50% R.V.)	2 mm after 24 h
Density: ISO 1183	1,63 g/ml
Processing temperature	+5°C - +40°C
Room temperature at application	+15°C - +35°C
Adhesive temperature	+15°C
Shelf life in original packing in dry conditions between +5°C - +25°C	12 months
Shore A hardness : ISO 868	45
Elongation at break : ISO 37	200%
Modulus at break : ISO 37	1,3 N/mm ²
Shearing force: DIN 53283	1,4 N/mm ²
Solvent & isocyanate content	0%
Dry matter content	ca. 100%
Temperature resistance	-40°C - +90°C
Extremely good moisture resistance and not sensitive to frost	

PACKING AND COLOUR
Bucket 15 kg - 33 buckets/pallet
Bucket 2 x 7,5 kg - 33 buckets/pallet
Box 3 x 7,5 kg - 36 boxes/pallet
Beige

METHOD OF USE

Preparation

- The substrate must be solid, sufficiently strong, clean, free of dust and grease and free of loose layers. Remove irregularities such as old adhesive residues mechanically. Preferably roughen/sand smooth surfaces to increase the contact surface.
- It is recommended to always perform an adhesion test on every surface. It is the user's responsibility to check whether the product is suitable for its application. Consult our technical service if necessary.

This technical data sheet replaces all previous editions. The data on this sheet have been compiled according to the last laboratory report. Technical characteristics can be changed or adapted. We are not responsible for any incomplete information. Before use, one needs to ensure that the product is suitable for his application. Therefore, tests are necessary. Our general conditions apply.

- Any cracks or fissures must be repaired with synthetic mortar that can be obtained by mixing **Hydroblocker 2K** with quartz sand.
- Cementitious screeds with high residual moisture can be treated with **Primer PU Turbo** (max. 4% residual moisture) or **Hydroblocker 2K** (max. 5% residual moisture).
- Surfaces that are not sturdy or compact enough must be reinforced with **Primer WB**, **Primer PU Turbo** or **Hydroblocker 2K**.
- Existing ceramic, granite, marble or similar floors should be properly degreased and then mechanically scratched. In case of rising damp, they must be treated with a three-component primer **Hydroblocker 3K**.
- In any case, do not apply a moisture barrier to screeds with underfloor heating, any residual moisture present will have to be removed by switching on the heating system, prior to installation.
- The moisture content of the substrate should be measured using a carbide meter and be compared to the maximum value as specified by the flooring manufacturer. In accordance with TV 272 of the BBRI, this is a maximum of 2.5% for cement screed and 0.5% for anhydrite; and in the presence of underfloor heating, 1.8% and 0.3% respectively.
- Uneven floors should be levelled first using a levelling layer like **DL Egaline** or **DL Maxi Egaline**.
- Preferably let the parquet acclimatize for a few days in the original packaging in the relevant room. Check the moisture of the wood before installation and compare it with the value prescribed by the manufacturer. Installation is strongly discouraged below 7% or above 11% wood moisture.
- Underfloor heating must have dilated at least 48 hours before installation.

Primer Extremely absorbent supports should be primed beforehand with **Primer WB** or **Primer PU Turbo**.

Parquet sizes

- Solid parquet: suitable for dimensions up to 150 mm wide and 14 mm thick and slenderness factor up to 10.7 (tested on solid oak according to NF B54 008 - report FCBA). Adhesive consumption for solid parquet up to 150x14mm: 1000g/m² (B11 comb).
- Composite parquet: suitable for all composite parquet that complies with the EN 1349 standard.

Application

- Use in well-ventilated rooms. Good ventilation is important during application and vulcanisation of the product.
- **Parabond Parquet 340** should be applied to the substrate with an adhesive scraper. Apply the adhesive with a coarsely serrated adhesive trowel.
- The adhesive exposure time is approximately 30 minutes (at 23°C and 50% R.H). It is therefore important not to apply too much adhesive in one stroke. Slide the parquet into the wet adhesive on the substrate and tap with a rubber hammer. The material can at this stage still be adjusted, just push it down well.
- If necessary, the parquet could be slightly loaded to ensure perfect spread of the adhesive. Many wood species should be tamped down from above. Parquet without tongue and groove should be rolled down using a cylinder roller.
- The gap between the wall and the parquet must be at least 10-15 mm.
- After 24 hours, walking on parquet and sanding can be done.

Consumption in full-surface bonding

700 - 900 g/m ² with B3 serrated trowel	Pre-manufactured parquet systems/planks, lamparquet, mosaic parquet
900 - 1200 g/m ² with B11 serrated trowel	Solid parquet, pre-manufactured laths/panels, industrial parquet, chip board, OSB

For bonding long, wide planks and in case of bonding upon uneven supports, it may be necessary to use a trowel with coarse serration to prevent hollow areas in the adhesive base.

Tooling If desired, smooth finishing can be done using **DL 100** or **scraper**.

Cleaning

Any adhesive that may protrude along the edges can be removed using a stopping knife. Adhesive residue that has not yet dried, can be removed using **Parasilico Cleaner**, dried glue can only be removed mechanically.

SAFETY Please consult the safety data sheet at www.dl-chem.com.

LIMITATIONS

- As there is an extended range of parquet floors on the market (pretreated or not), you have to make sure that the product is suitable for the intended application; if necessary the product has to be tested beforehand on the material.
- Do not use on PE, PP, PA, Teflon® and bitumen supports and on bases treated with certain soaking agents containing synthetic materials.
- Not suitable for permanent immersion.

This technical data sheet replaces all previous editions. The data on this sheet have been compiled according to the last laboratory report. Technical characteristics can be changed or adapted. We are not responsible for any incomplete information. Before use, one needs to ensure that the product is suitable for his application. Therefore, tests are necessary. Our general conditions apply.

TECHNICAL APPROVALS

- FCBA Report N° 2021.226.1147
- GEV EMICODE: EC1plus certificate



* Information sur le niveau d'émission de substances volatiles dans l'air intérieur, présentant un risque de toxicité par inhalation, sur une échelle de classe allant de A+ (très faibles émissions) à C (fortes émissions).

This technical data sheet replaces all previous editions. The data on this sheet have been compiled according to the last laboratory report. Technical characteristics can be changed or adapted. We are not responsible for any incomplete information. Before use, one needs to ensure that the product is suitable for his application. Therefore, tests are necessary. Our general conditions apply.