



**CHARACTERISTICS**

- One-component, ready to use, high temperature resistant sealant
- Heat resistant to 1250°C
- Can be overpainted after vulcanisation

**APPLICATIONS**

- Specifically designed for permanently repairing and sealing joints cracks and fissures around fireplaces, fire stoves, chimneys and ovens.
- Offers good adhesion to metal, brick and concrete surfaces. No primer needed.
- Indoor use only.

TECHNICAL CHARACTERISTICS	
Appearance	Paste
Application temperature	Between +5°C and +40°C
Skin forming time (23°C and 50% R.H.)	30 min.
Shore A hardness: ISO 868	90
Shrinkage	<15%
Density	1,9 g/ml
Heat resistance	Up to 1250°C
Joint movement: ISO 11600	3%
pH	10
Shelf life, in original packing in dry conditions between +5°C - +25°C	Min. 9 months

PACKING AND COLOURS
25 cartridges of 310 ml/box - 48 boxes/pallet
Anthracite

**METHOD OF USE**

**Preparation:** All surfaces must be clean and free from grease. Metal surfaces should be cleaned and degreased with Para-silico Cleaner. When used in conjunction with most common construction substrates, a primer is not required.

**Application:** With a gun (manual or pneumatic). The shape of the joint is important. Avoid thin layers.

**Tooling:** The joint should be tooled within 5 minutes of application to ensure good contact between sealant and the substrate. Tooling of the sealant also gives a smooth, professional finish.

**Cleaning:** Uncured material can be removed by wiping a dampened cloth. Cured material can be carefully removed by abrasion or other mechanical means.

**SAFETY** Safety data sheet available on request.

**LIMITATIONS**

- Not recommend for use in central heating systems or gas pipes.
- Only for interior use.
- Application to electrical devices can be dangerous (in connection with the conductivity of the product).

**TECHNICAL APPROVALS**



\* Information sur le niveau d'émission de substances volatiles dans l'air intérieur, présentant un risque de toxicité par inhalation, sur une échelle de classe allant de A+ (très faibles émissions) à C (fortes émissions).

This technical data sheet replaces all previous editions. The data on this sheet have been compiled according to the last laboratory report. Technical characteristics can be changed or adapted. We are not responsible for any incomplete information. Before use, one needs to ensure that the product is suitable for his application. Therefore, tests are necessary. Our general conditions apply.