



CHARACTERISTICS

- Joint sealing tape
- Made of polyurethane soft foam with acryl dispersion impregnation
- Self-adhesive on one side
- Pre-compressed (to one fifth of its original thickness)
- On rolls of different length, varying according to the thickness
- Rainproof up to at least 300 Pa (*)

APPLICATIONS

- Window construction
 - Heavy rain tight connection joints
 - Thermal sealing between the window frame and the masonry, profile coupling, backfilling, window pillars
- Façade technology
 - Support for in-situ concrete/concrete element
 - Boarding connection when concreting
- Interior work
 - Light partitions
 - Decoupling of double floors
- High-pitched/flat roof
 - Roof area window
 - Pantile sealing
 - Ridge/groin/groove/dormer window

| TECHNICAL CHARACTERISTICS | |
|--|--|
| Colour | Grey |
| Fire behaviour EN 13501 | E at 50% compression |
| Temperature resistance | -30°C - +100°C, briefly max. 130°C |
| Joint permeability EN 12114 | $a^n \leq 1 \text{ m}^3/[\text{h.m}(\text{daPa})^{2/3}]$ |
| Heavy rain tightness EN 1027 | $\geq 300 \text{ Pa}$ |
| Tensile strength : ISO 1798 | $> 60 \text{ kPa}$ |
| Elongation at break : ISO 1798 | $> 180\%$ |
| Compressive strain deformation properties : ISO 3386 | Ca. 2,3 kPa |
| Storage | 24 months |

| PACKING AND MEASUREMENTS | | | |
|----------------------------------|---|------------------------|----------------------|
| Width of Pressband = joint depth | Specific application area = joint width | Maximum expansion (**) | Packing |
| 10 mm | 1,5 – 2,5 mm | $10 \pm 1 \text{ mm}$ | 30 rolls of 18 m/box |
| 15 mm | 1,5 – 2,5 mm | $10 \pm 1 \text{ mm}$ | 20 rolls of 18 m/box |
| 15 mm | 2 - 4 mm | $15 \pm 1 \text{ mm}$ | 20 rolls of 12 m/box |
| 20 mm | 2 - 4 mm | $15 \pm 1 \text{ mm}$ | 15 rolls of 12 m/box |

* Within a specific application area: see the “Packaging and Measurements” table.

** Depending on the ambient and material temperature and the age of the tape.

This technical data sheet replaces all previous editions. The data on this sheet have been compiled according to the last laboratory report. Technical characteristics can be changed or adapted. We are not responsible for any incomplete information. Before use, one needs to ensure that the product is suitable for his application. Therefore, tests are necessary. Our general conditions apply.








METHOD OF USE

Preparation

- Make sure the surrounding materials are compatible.
- The choice of the dimensions of **Pressband Acryl** must correspond to the actual (max.) width of the area that needs to be sealed. Take into account the variations in the joint width depending on temperature or movement.
- The expansion behavior of the sealing tapes depends on the ambient and material temperatures (Eventual the tapes to acclimatize before application) and the age of the tape.
- Expansion slows down with cold temperatures.
- The surface must be as flat as possible, clean, dustfree and wind dry. The joints must be as parallel as possible (in certain cases a replastering or reprofiling of he the joints in old building can be necessary). The specific application area may not be exceeded or diminished, not even on uneven surfaces.

Application

- Cut the first 2 cm off the band.
 - Remove approximately 20-30 cm from the back strip and place the tape in the joint parallel to the edge and 1-2 mm from the edge.
1. Press the adhesive side of the tape into the joint (eg. with a spatula) and continue to press lightly, bit by bit by just pressing gently. If necessary, attach the end of the tape to the roll with a clip or adhesive tape. The tape may never be stretched!
 2. When installing expanded tape, place the tape along the total length of the joint and cut the tape 2-3% longer than the total length of the joint. Stick the tape in the correct place and fix the material with the tape, if necessary with a clamp. The compression applied determines the specific application area and thus the effectiveness of the seal.
 3. **Cross joint or T-joint:** First attach the vertical tape in 1 piece and then work with the horizontal tapes from the outside corners inwards.
 4. **Corners:** To avoid leaking joints, never put the tape around the corners, but place it as shown in the drawing. Form a corner with the tape.
 5. **Connection:** Gently press the tapes together. Never twist or overlap.
 6. **Varying joint widths:** When the width of the joints show considerable differences, the use of sealing tapes in different sizes is recommended. Never overlap the ends.
 7. **Moist or dirty joints:** If the tape does not stick sufficiently on damp, dusty or ice-cold joints, clamp the tape at various points with wedges. Remove the wedges after expansion.



Cleaning

Clean hands with soap and water.

Adhesive residue can be removed with **Parasilico Cleaner**.

Storage

The storage stability is 24 months from the production date. Store cool and dry in the original packaging at + 5°C - +25°C. Only store cardboard boxes upright (with the rolls lying down). Store and transport individual rolls exclusively on the entire surface. Avoid local load on the rollers. Avoid shifting the individual layers. Avoid mechanical insertion on the compressed roll. Rolls in opened cardboard boxes must be weighted to prevent them from expanding (telescoping). Mechanical load (in particular perpendicular to the roll and pressure load on the roll side) can cause the individual layers of the compressed roll to shift and cause the rollers to expand.

SAFETY

On the basis of existing data and experience, the product is not hazardous material in the meaning of the Hazardous Material Regulations, and the corresponding EC directives. We recommend however that you take the same care and use the same hygiene as with chemical materials.

This technical data sheet replaces all previous editions. The data on this sheet have been compiled according to the last laboratory report. Technical characteristics can be changed or adapted. We are not responsible for any incomplete information. Before use, one needs to ensure that the product is suitable for his application. Therefore, tests are necessary. Our general conditions apply.