



## CHARACTERISTICS

- Waterproof coating
- Forms a waterproof membrane, resistant to positive and negative waterpressure

## APPLICATIONS

- Indoor and outdoor use.
- Interior and exterior waterproofing of foundations, basements, ponds, water reservoirs, consisting of porous mineral building materials such as cement and concrete blocks.

## TECHNICAL CHARACTERISTICS

Type of product	White cement
Consistency	Liquid pasta
Drying time (depending on the layer thickness and atmospheric conditions)	24 hours
Application temperature	+5°C - +35°C
Shelf life of unopened product	18 months
Storage conditions	Transport and store upright in a dry, cool place at +5°C to +25°C.

## PACKING AND COLOURS

**barrel 25kg - 22 pieces/pallet**  
White

## METHOD OF USE

### Preparation

- Remove all loose and foreign substances that may hinder proper adhesion, such as old cement layers, paint, plaster, salts, oils, molds, using a high-pressure washer, wire brush, chisel, etc.
- Thoroughly rinse the prepared surface with water to remove all loose residues and dust.
- Dilute the product with clean tap water (1 part water to 5 parts product) and stir until a lump-free mixture is obtained. The basement brush should be held at a slight angle, just short of tipping into the mixture.
- Allow the diluted mixture to rest for 15 minutes, then stir vigorously again.
- Always pre-wet the surface but avoid forming droplets.
- Do not prepare more product than can be applied in approximately 45 minutes to avoid the product becoming too dry during application.

### Application

- Apply in a crisscross pattern with a brush to a thickness of 1 mm.

This technical data sheet replaces all previous editions. The data on this sheet have been compiled according to the last laboratory report. Technical characteristics can be changed or adapted. We are not responsible for any incomplete information. Before use, one needs to ensure that the product is suitable for his application. Therefore, tests are necessary. Our general conditions apply

- Apply a second coat after the complete drying ( $\pm 24$  hours) of the first coat. Pre-wet the surface lightly again.

### Consumption

1.5 to 2 kg/m<sup>2</sup> per layer

### Tooling

- For a drinking water reservoir, swimming pool, or fish pond, the lining must be washed with a salt solution (brine, 12.5% salts in water) after hardening.

### Cleaning

- Before curing: Tools, surfaces and uncured residues can be removed with water.

## SAFETY

Consult the safety information on the packaging and the safety data sheet for more information.

## POINTS OF ATTENTION

- Do not use on masonry.

This technical data sheet replaces all previous editions. The data on this sheet have been compiled according to the last laboratory report. Technical characteristics can be changed or adapted. We are not responsible for any incomplete information. Before use, one needs to ensure that the product is suitable for his application. Therefore, tests are necessary. Our general conditions apply