



CHARACTERISTICS

- Primer for silicone sealant
- Promotes the adhesion of silicone sealant to the substrate
- The treated surface may be durably subjected to damp influences without the danger of saponification

APPLICATIONS

- Fixing dusty and absorbent surfaces.
- Suitable for use on porous surfaces, including alkaline surfaces.
- Only suitable for professional use.

TECHNICAL CHARACTERISTICS

Type of product	Acrylate copolymer resin dissolved in toluene
Density (g/ml)	0.95
Drying time (depending on the layer thickness and atmospheric conditions)	60 minutes
Application temperature	+5°C - +25°C
Flash point (CC, degrees C)	+8 (DIN 51755)
Shelf life of unopened product	12 months
Storage conditions	Store in a dry, cool place at +15°C to +25°C.

PACKING AND COLOURS

26 x can 250ML/box - 1664 pieces/pallet

Transparent

can 1l - 104 pieces/pallet

Transparent

METHOD OF USE

Preparation

- The surfaces must be solid, dry and free of dust and grease.
- If needed degrease the materials to be glued with Parasilico Cleaner, MEK, fire alcohol, ethanol.

Application

- Apply the primer to the surface with a paint brush.
- A second coat may be necessary for very porous substrates.
- When the primer is dry, apply the silicone sealant. The faster after drying, the better. Apply the silicone sealant within 16 hours at the latest. If this time period has been exceeded, a new layer of primer must be applied.

This technical data sheet replaces all previous editions. The data on this sheet have been compiled according to the last laboratory report. Technical characteristics can be changed or adapted. We are not responsible for any incomplete information. Before use, one needs to ensure that the product is suitable for his application. Therefore, tests are necessary. Our general conditions apply

SAFETY

Consult the safety information on the packaging and the safety data sheet for more information.

This technical data sheet replaces all previous editions. The data on this sheet have been compiled according to the last laboratory report. Technical characteristics can be changed or adapted. We are not responsible for any incomplete information. Before use, one needs to ensure that the product is suitable for his application. Therefore, tests are necessary. Our general conditions apply